



No-heat spray polyurethane foam insulation

SPECIFICATIONS

MATERIAL SUPPLIER

Burtin Polymer Laboratories (BPL)

INDUSTRY

Spray polyurethane foam insulation

APPLICATION

Attic air sealing, rim joist, touch-up

MATERIAL SPECS

- Two-pound room temperature foam
- BPL Part Number: 1420-2-MI-13

Typical Properties

- Ratio: 1:1
- Viscosity at 75°F (24°C):
- Side A: approximately 250 cps
- Side B: approximately 250 cps
- Application temperature range: 75-110°F (24-43°C)
- Colors:
 - Side A: Dark brown
 - Side B: Dark green

GRACO EQUIPMENT*

- Reactor E-8p Portable Plural Component Sprayer

CONFIGURATION

- Hose length (non-heated hose): 35 ft (10.6 m) standard, 105 ft (32 m) maximum
- Recommended spray guns (round and flat pattern): Fusion AP, Fusion CS, P2 (00 max mix chamber size for all recommended spray guns)
- Weight: 95 lb (43 kg)
- Max output: 12 lb/min (5.44 kg/min)

Additional Information:

Round pattern mix chambers produce the best pattern/mix at temperatures above 75°F. If round pattern and/or mix is poor at 75°F, switch to a 00 flat mix chamber and medium flow FT0438 flat tip for improved results. Different tip sizes can be used to achieve desired results.

For best results, follow chemical manufacturer's application recommendations.



Lightweight and compact, the Reactor E-8p is the best choice for portability and high-quality spray foam.



**Exact equipment configuration will vary and depend on factors such as rate of output, length and size of hoses.*

For more information, contact us at 1-877-844-7226 or info@graco.com. Visit us at www.graco.com

PROVEN QUALITY. LEADING TECHNOLOGY.

© 2011 Graco Inc. 348567 Rev. A 9/11 All written and visual data contained in this document are based on the latest product information available at the time of publication. Graco reserves the right to make changes at any time without notice. All other brand names or marks are used for identification purposes and are trademarks of their respective owners.